


RAHUL ENGINEERS LABORATORY

(A Govt. of Rajasthan Regd. MSME Unit)

ISO 9001:2015 & ISO/IEC 17025:2005 Certified Laboratory

MSME080262200005
Udhog Adhar No. - RJ33E0009668
GSTIN - 08AEVPP3102K1Z5
PAN - AEVPP 3102 K



FACILITIES : Testing of Cement, Aggregate, Bricks, Concrete, TMT Steel Bar, Paver Block, Bitumen, Bituminous Mix, Soil, Sand, Rock, Water, Ores & Minerals, Quartz, Feldspar, Soapstone, Diatomaceous / Siliceous Earth, Lime Stone, Dolomite, China Clay, Iron Ore & Bauxite

5-A, Chitrakut Nagar, Bhuwana By-pass Road, Udaipur (Raj.) PIN 313 001, INDIA, Tel. : +91-294-2440317
Cell : +91 6350324167, +91 8107343935, E-mail : rahul.labudr@gmail.com, Website : www.rahulengineers.com

Report No:-REL-Mech. /191105-1

Date :- 06.11.19

TEST REPORT

1	Name of Customer	:	Rudra Stones Exports, Dabok, Udaipur Rajasthan India Pin- 313022
2	Customer Contact No.	:	Mr. Yogesh Nagda- 7339923388 (rudrastonesexports@gmail.com)(info@rudrastonesexports.com)
3	Customer Reference No.	:	Order Slip, Dated:- 02.11.19
4	Type of Sample	:	Black Galaxy Granite
5	Sample Identification	:
6	Date & Mode of Receipt of Sample	:	02.11.19, Sample submitted by customer.
7	REL Job No.	:	REL-191105-1
8	Name of Work	:	Testing of Black Galaxy Granite Sample.
9	Location	:	Ongole, Andhra Pradesh (India)
10	Date of Sampling	:
11	Date of Testing	:	02.11.19 to 05.11.19

Test Results:-

Lab Job No.	Water Absorption IS:2386 (Pt-3)1963 (RA-2016) (%)	Flexural Strength (Modulus of Repture) IS 1121(Pt-2), 1974 (RA-2003) (kg/cm ²)		Remarks
		Individual	Average	
REL-191105-1	0.02	352.93	334.43
		326.50		
		323.85		

Tested By:

(J.L. Paliwal)
Scientist

Issued By:

(M.P. Jain)
Gen. Manager

LABORATORY

Note: - 1. Test report is authentic only if contains hallmark & seal.

2. The test results refer only to the samples received in the Laboratory.
3. This report shall not be reproduced except in full without written approval from Rahul Engineers Laboratory.
4. Rahul Engineers Laboratory shall not in any way be involved in any action following the interpretation of test results.
5. Any discrepancy in test results should be reported within 15 days.
6. Subject to Udaipur Jurisdiction only.

End of Report